

1300 Eye Street N.W.
Washington, DC 20005
Telephone: 202.659.0100
Facsimile: 202.659.0105
www.novakdruce.com

**Novak Druce DeLuca
& Quigg, LLP**

RECEIVED
CENTRAL FAX CENTER

MAY 23 2006

Fax

To:	USPTO - Mail Stop ISSUE FEE	From:	Novak Druce DeLuca & Quigg
Fax:	(571) 273-8300	Pages:	3
Phone:	(571) 272-1000	Date:	May 23, 2006
Re:	Docket No. 54251	cc:	

☐ Urgent ☐ For Review ☐ Please Comment ☐ Please Reply ☐ Please Recycle

• Comments:

In re Application of: CIPRIAN, et al.

Serial No.: 10/765,988

Filing Date: January 29, 2004

Attachments: COMMENTS ON STATEMENT OF REASONS FOR ALLOWANCE

BEST AVAILABLE COPY

CONFIDENTIALITY NOTICE: This facsimile and any attachments contain information from the law firm of Novak Druce DeLuca & Quigg, LLP, which may be confidential and/or privileged. The information is intended to be for the use of the individual or entity named on this facsimile. If you are not the intended recipient, be aware that any disclosure, copying, distribution or use of the contents of this facsimile is prohibited. If you receive this facsimile in error, please notify us by reply facsimile immediately so that we can arrange for the retrieval of the original documents at no cost to you.

MAY 23 2006

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

IN RE APPLICATION

DOCKET No.: PF++54251

OF: CIPRIAN ET AL.

CONFIRMATION No.: 2865

SERIAL No. 10/765,988

GROUP ART UNIT: 1624

FILED: JANUARY 29, 2004

EXAMINER: Z. C. TUCKER

FOR: DECOLORATION AND COLOR STABILIZATION OF TEDA SOLUTION

I hereby certify that this correspondence is being
facsimile transmitted on the date indicated below to
Commissioner of Patents and Trademarks, Alexandria,
Va 22313-1450, at:

(571) 273-8300

Extension No.
or is being deposited with the United States Postal
Service with sufficient postage as first class mail
in an envelope addressed to Commissioner for Patents
and Trademarks, Alexandria, Va 22313-1450,
on:

Date of Transmission/Deposit: May 23, 2006
Person Making Transmission/Deposit: SLAWOMIR MOSIOLEK
Signature: *Slawomir Mosiolek*

Mail Stop Issue Fee
Honorable Commissioner
for Patents
P.O. Box 1450
Alexandria, VA 22313-1450

COMMENTS ONSTATEMENT OF REASONS FOR ALLOWANCE

Sir:

The following Comments are made in view of the Examiner's Statement of Reasons for Allowance enclosed with the Notice of Allowance issued on February 23, 2006.

C O M M E N T S

The Examiner inter alia remarked that the closest prior art Lang et al. (US 6,552,194) taught some different solvents as TEDA quench liquids and suggested that polyhydric alcohols could be employed for that purpose. For clarification the following is respectfully noted.

Lang et al. as well as applicants invention relate to a process for the preparation of highly pure triethylenediamine (TEDA) or solu-

060517

- 1 -

BEST AVAILABLE COPY

Serial No. 10/765,988

CIPRIAN et al.

PF++54251

tions thereof. The processes are similar with regard to the initial steps, ie. vaporizing TEDA and quenching the TEDA vapor in a solvent.

Lang et al. propose a variety of possible solvents for this purpose, including aliphatic, chlorinated and aromatic hydrocarbons, alcohols, ethers and polyether alcohols.¹⁾ Where the TEDA solution is to be used directly as a catalyst solution for the production of polyurethane foam it is necessary that the solvent be an alcohol or a polyetheralcohol and, additionally, that the solution have a low color number. According to Lang et al., a solution of 33% weight of TEDA quenched in dipropylene glycol has a color number of less than 150, preferred less than 100 APHA.²⁾ In order to arrive at highly pure TEDA and at TEDA solutions which exhibit lower color numbers, further purification of the TEDA solution is required.

According to Lang et al., this additional purification can be achieved by crystallization of the TEDA from the solution, and the recrystallized TEDA can be redissolved for further use.³⁾ Where the crystallization of the TEDA is intended, the solvent used for the TEDA quench is preferably an aliphatic hydrocarbon.⁴⁾

The process disclosed and claimed by applicants solves the problem of preparing a TEDA solution in alcohols/polyether alcohols which exhibit low color numbers and long stability during storage by quenching the TEDA vapor directly in the alcohol/polyether alcohol and by subsequently treating the TEDA solution with adsorbents.⁵⁾ After the adsorbents have been removed from the TEDA solution, the solutions can be used further without an additional purification being necessary. The TEDA solutions which are obtained in accordance with applicants' procedure exhibit low color numbers (50 APHA) and long storability without large changes of the color numbers.⁶⁾ Applicants' process has the advantage that the amount of solvent which is needed to obtain TEDA solutions meeting the requisite purity requirements are significantly reduced.

The foregoing explanations show that applicants' process is distinctly different from the procedure which is disclosed by Lang et al.

1) Cf. col. 4, indicated lines 46 to 64, of US 6,552,194.

2) Cf. col. 4, indicated line 65, to col. 5, indicated line 5, of US 6,552,194.

3) Cf. col. 2, indicated lines 65 to 68, of US 6,552,194.

4) Cf. col. 5, indicated lines 6 to 10, of US 6,552,194.

5) Cf. page 4, para. 3, of the application.

6) Cf., e.g., Examples 3 to 5, pages 13 to 15, of the application.

060517

- 2 -

BEST AVAILABLE COPY

Serial No. 10/765,988


CIPRIAN et al.

PF++54251

Please charge any shortage in fees due in connection with the filing of this paper, including Extension of Time fees, to Deposit Account No. 14.1437. Please credit any excess fees to such deposit account.

Respectfully submitted,

NOVAK DRUCE DELUCA & QUIGG



Jason D. Voight

Reg. No. 42,205

1300 Eye Street, N.W.
Suite 400 East Tower
Washington, D.C. 20005
(202) 659-0100

JDV/BAS

BEST AVAILABLE COPY

060517

- 3 -